

In the Claims:

Please cancel claim 9, without prejudice.

Please amend claims 1, 3, 6, 7 and 10 as follows:

1. (Currently amended) A method for manufacturing a liquid crystal panel of an active matrix system, comprising the steps of:

performing arraying for plotting a master glass substrate into a plurality of blocks, further plotting each block into ~~one, alternatively a plurality of~~ at least one device-forming ~~regions~~region, and forming a conductive film, an insulating film and a semiconductor film which constitute TFT (Thin Film Transistor) in the device-forming region;

performing primary cutting for cutting the master glass substrate into the respective blocks to form a plurality of sub-TFT substrates;

performing sub-TFT substrate processing for executing processing for each sub-TFT substrate in accordance with a device to be manufactured; and

performing secondary cutting for cutting the sub-TFT substrate into ~~each of the~~ device-forming ~~regions~~regions,

wherein said sub-TFT substrate processing step includes a step of forming a semiconductor film above the sub-TFT substrate.

2. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein only liquid crystal panels having identical sizes are formed in each block of the master glass substrate.

3. (Currently amended) A manufacturing method of a liquid crystal panel according to claim 1, wherein at least two, ~~alternatively more~~ kinds of liquid crystal panels different from each other in size are formed in each block of the master glass substrate.

4. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein said sub-TFT substrate processing step includes the steps of: forming a pixel electrode above the sub-TFT substrate; forming an orientation film for covering the pixel electrode; and joining a second substrate onto the sub-TFT substrate, and after the secondary cutting step, a step of sealing a liquid crystal between the sub-TFT substrate and the second substrate after the cutting is provided.

5. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein said arraying step includes the steps of: forming an amorphous silicon film above the master glass substrate; and converting the amorphous silicon film into

a polysilicon film by irradiating the amorphous silicon film with a rectangular laser beam and moving the laser beam in one direction.

6. (Currently amended) A manufacturing method of a liquid crystal panel according to claim 1, wherein said sub-TFT substrate processing step includes at least one of the steps of: performing corner cutting for the sub-TFT substrate after the primary cutting; and performing end face processing for ~~the same~~ the sub-TFT substrate after the primary cutting.

7. (Currently amended) A manufacturing method of a liquid crystal panel according to claim 1, ~~wherein for forming liquid crystal panels having united driving circuit of plural kinds and different size by using the master glass substrate, arranging directions of the driving circuits are identical to one another with respect to a display section of each liquid crystal panel~~ wherein, when plotting each block into the device-forming region, the device-forming region is plotted to include a display section and a driving section of a liquid crystal panel having a united driving circuit, where an extending direction of the driving section with respect of the display section is substantially identical among each of the blocks.

8. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein in said sub-TFT

substrate processing step, pattern alignment is performed by fusing a fiducial mark provided for each sub-TFT substrate.

9. Canceled.

10. (Currently amended) A manufacturing method of a liquid crystal panel according to ~~claim 9~~claim 1, wherein in at least one of the plurality of blocks, a photoelectric conversion element using a semiconductor film is formed.

11. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein direct-vision liquid crystal panels are formed in all of the plurality of device-forming regions.

12. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein direct-vision liquid crystal panels are formed in the plurality of device-forming regions, and a projection panel type is formed in the other device-forming region.

13. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein a liquid crystal panel of a transmission type is formed in a part of the plurality of device-forming regions, and a projection panel of a reflection type is formed in the other device-forming region.

14. (Original) A manufacturing method of a liquid crystal panel according to claim 1, wherein in at least one of the plurality of device-forming regions, a liquid crystal panel with a built-in image sensor is formed.

15-17. (Canceled)